



1. Product description

KEIM Contact-Plus-Grob is a filling silicate based priming coat ideal for renovation work containing glass fibers and high-grade fillers in balanced grain sizes and shapes.

2. Field of application

KEIM Contact-Plus-Grob is used as a bonding bridge between sound, existing organically bound coatings and subsequent coats of KEIM silicate emulsion paints and/or for filling hairline cracks up to 1 mm in width and for equalizing differences in substrate texture.

Old coatings not suitable for coating with KEIM Contact-Plus-Grob are plasto-elastic coatings or coatings susceptible to saponification (e.g. certain oil paints).

3. Product properties

- Bonding bridge between an existing organic substrate and subsequent coats of KEIM silicate emulsion paints
- Closes cracks (up to max. 1.0 mm in width)
- Equalizes textures
- Non-film-forming
- UV-resistant
- Non-flammable

Material characteristics

- Specific weight: approx. 1.70 g/cm²
- Vapor diffusion resistance: $s_d = 0.02$ m
- Max. grain size: 1.0 mm
- pH-value: approx. 11.4

Color shade

White

4. Application instructions

Substrate preparation

The substrate must be sound, dry, clean and free of dust and grease. Any loose areas of existing organically bound coatings and dirt should be removed either mechanically or by water jetting. Use KEIM Spachtel, KEIM Concretal-Feinspachtel, KEIM Leichtpachtel, or KEIM UniversalPutz to make good any damaged areas. The existing coating must be completely removed wherever filler is to be applied.

Application

On non-absorbent substrates, apply KEIM Contact-Plus-Grob evenly by brush, always undiluted, using criss-cross strokes.

On absorbent substrates, the product may, if necessary, be diluted with up to 10% (25 kg with 2.5 l / 0.66 gal of dilution) of KEIM Fixativ, KEIM Spezial-Fixativ or KEIM Concretal-Fixativ.

Subsequent coats

KEIM Contact-Plus-Grob must always be overcoated with two subsequent coats of paint, for example with KEIM Granital or KEIM Concretal-W, e.g.:

Intermediate coat: KEIM Granital diluted (max. 2 l / 0.5 gal of KEIM Spezial-Fixativ per 10 kg),

Finishing coat: KEIM Granital undiluted.



Application conditions

Ambient and substrate temperature $> + 5^{\circ}\text{C}$ (41°F). Do not apply in direct sunlight or onto sun-heated substrates. Protect coated surfaces from direct sunlight, wind and rain during and after application.

Drying times

A drying time of at least 12 hours must be left between coats

Consumption

On a smooth, non-absorbent substrate for a filler coat: approx. 0.5 kg of KEIM Contact-Plus-Grob.

On a smooth, absorbent substrate: approx. 0.6 kg of KEIM Contact-Plus-Grob.

The stated consumption values are for guidance and depend on the nature of the substrate and the application method. Exact consumption values can only be determined by painting trial areas on the structure to be coated.

Cleaning of tools

Clean with plenty of water immediately after use.

5. Packaging

5 kg and 25 kg containers

6. Storage

Shelf life is approx. 12 months in a sealed container under cool, frost-free conditions.

7. Hazardous substances ordinance class

n/a

8. Transport hazard class

n/a

9. Disposal

EC Waste Code No. 08 01 12.

Any residues must be emptied out of containers before recycling.

10. Safety instructions

The mineral binder has an alkaline action. Provide appropriate protection for surfaces which are not to be coated (e.g. glass, natural stone, ceramics etc.). Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with plenty of water. Protect the eyes and skin from splashes. Keep out of reach of children.

Product code: M-SK 01

The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release those purchasing and applying our products from the duty of establishing for themselves, with due care, the suitability of our products for the intended application. Standard building industry practices must be complied with. We retain the right to make modifications to improve the products or their application. This edition supersedes all earlier editions.

