

KEIM LASUR

TECHNICAL INFORMATION

1 Field of application

KEIM Lasurs are suitable for all types of unpainted mineral substrates.

KEIM Restauro Lasur for render, brickwork and stone surfaces, diluted with KEIM Restauro Fixativ.

KEIM Concretal Lasur for concrete surfaces diluted with KEIM Concretal Dilution.

2 Product properties

- Water vapour permeable
- Colourfast
- Resistant to mould and fungal growth
- Easily cleaned
- Free from solvents and biocides
- Unifies colour
- Non-flammable
- Cradle to Cradle Certified®

KEIM Restauro/Concretal Lasur s_d : ≤ 0.01 m

VOC Content: 0-4g/l VOC

3 Application instructions

Substrate preparation

All loose, flaking and unstable material must be identified and then thoroughly removed, all surfaces must be thoroughly washed down with clean cold water to remove all surface dirt and dust.

Application

The specification of KEIM Lasurs will vary according to the specific type of substrate.

A typical specification would be a two coat system; the first coat to be the appropriate Dilution/Fixativ applied by brush and worked well into all surfaces.

After a minimum period of 12 hours a second coat of KEIM Lasur in the chosen colour should be applied, diluted to the required level with the appropriate Dilution/Fixativ.

Additional coats may be applied in the same manner as the second coat, or with slight variations and colours, dependent on the desired finish.

We would always suggest that site trials are conducted to determine the desired colour and number of coats and the ratio of Fixativ/Dilution required to obtain the desired opacity and determine consumption rates.

Cleaning of tools

Clean immediately after use with water.

4 Packaging

5lt & 15lt containers

