



TECHNICAL DATA SHEET

GUTEX THERMOWALL-L

1. PRODUCT DESCRIPTION

Wood fiber insulation boards in accordance with DIN EN 13171, fire behaviour: E according to EN 13501.

2. FIELD OF APPLICATION

Facade insulation boards for KEIM external thermal insulation composite systems according to system approval: Z-33.43-942; Z-33.47-660

Generally approved by the building authorities for: exterior walls; window and door reveals.

Suitable for: Masonry or concrete, rendered and unrendered; panel material in timber construction.

Application type according to DIN 4108-10: WAP.

The complete ETIC system is normally inflammable B2 in accordance with DIN 4102-1. Permissible building height according to the State Building Code.

Not suitable for: Integration into the ground; horizontal and inclined surfaces exposed to weathering; metallic substrates; saponifiable existing substrates; substrates with salt efflorescences; plasto-elastic coatings; cold self-adhesive plastic membranes.

3. PRODUCT PROPERTIES

- with improved heat protection
- in a handy format
- effort saving processing due to light formulation
- from renewable resources
- fire behaviour: E according to EN 13501
- excellent heat storage capacity
- for increased sound insulation
- form- and pressure-stable
- sound in terms of building biology
- low environmental impact
- The insulation panels comply with the high standards of the VDPM e.V. (association for insulation systems, renders and mortars)

MATERIAL CHARACTERISTICS:

- | | |
|--|---|
| - CE marking code: | WF-EN13171-T5-WS1,0- DC(70,-)3-CS(10/Y)50-TR7,5- MU3-AFr100 |
| - Panel size: | 1200 x 400 mm |
| - Panel thickness: | 120 - 200 mm |
| - Edge formation: | square |
| - Water vapour diffusion resistance μ -value: | 3 |
| - Compressive strength: | ≥ 50 kPa |
| - Tensile strength perpendicular to the panel plane: | TR7,5 $\geq 7,5$ kPa |
| - Thickness tolerance: | T5 +3 / -1 mm |
| - Squareness: | S5 ± 5 mm/m |
| - Colour shade: | brown |

4. APPLICATION INSTRUCTIONS**SUBSTRATE PREPARATION:**

The substrate must be strong, dry, clean, sound and free from adhesion-reducing residues. Unevenness of up to 2 cm/m may be bridged. Larger unevenness must be mechanically levelled or by applying a render in accordance with DIN EN 998-1. Strongly sanding or unevenly absorbent surfaces should be primed with Indulaqua primer. Observe the Technical Data Sheet of the primer with regard to execution and dilution. To use the anchor on substrates that do not fall into the approved use categories, anchor pull-out tests must be carried out on the building and documented.

APPLICATION CONDITIONS:

Ambient and substrate temperature during application and drying from min. + 5 °C to + 30 °C. Do not apply in direct sunlight or on sun-heated substrates. Protect surfaces from direct sun, wind and rain during and after application.

APPLICATION:

Cut to size using an insulation knife or a suitable insulation saw.

GLUING:

The insulation panels are butted tightly and glued in a bond from bottom to top. Apply the appropriate adhesive mortar to the insulation panels using the bead-and-dot method or over the entire surface. Push the boards into place. At the edges of the building, the insulation panels are glued offset. On uncoated sides of insulating materials, a press filler must be applied. Closing of unavoidable defects and joints up to 5 mm wide with Iso Top Thermfoam B1 is permissible. General instruction with regard to gluing: Do not apply adhesive to the panel joints. Do not create an insulation panel joint over a joint in the substrate underneath.

DOWELING:

Check the adhesion of the insulation panels after at least 3 days. Insulation panels that are not bonded or damaged must be replaced. Anchoring is carried out in glued and dowelled ETICS systems using ETICS fasteners approved by the general building authorities or by the European authorities according to DIN EN 1991-1-4/NA. The required dowel quantity depends on the building height and the respective wind zone in which the object is located. For further information, please refer to our ETICS Technical Guide, Chapter #8, ETICS Wind Suction Loads. The minimum distance between anchor shank and board edge is min. 150 mm, the minimum distance between anchor shank and anchor shank is min. 200 mm.

REINFORCEMENT:

After a sufficient setting time of the adhesive, apply the mixed, system-specific reinforcing mortar evenly to the insulation panels, preferably with a 10 mm toothed trowel. Embed the system-specific Glasfaser-Gittermatte (glass fibre mesh), overlap the edges by 10 cm and fill wet-in-wet with system-specific reinforcing mortar. The system-specific Glasfaser-Gittermatte should be embedded in the middle (layer thicknesses up to 6 mm) or in the upper third (layer thicknesses from 6 mm). Thickness of the reinforcing layer depends on the respective system approval and can be in the range of approx. 5 - 10 mm.

5. PACKAGING / TECHNICAL DATA

Panel size [mm]	Panel thickness [mm]	edge	Pieces per unit	m ² per pallet	Bundle per pallet
1200 x 400	120	square	36	17.28	1
1200 x 400	140	square	32	15.36	1
1200 x 400	160	square	28	13.44	1
1200 x 400	180	square	24	11.52	1
1200 x 400	200	square	22	10.56	1

TECHNICAL DATA SHEET – GUTEX THERMOWALL-L

PACKAGING / TECHNICAL DATA ADDITIONAL INFORMATION:

120, 140 mm on request.

6. STORAGE

max. storage time	Storage conditions
no maximum storage time	dry protect against weathering protected from heat and direct sun.

STORAGE INFORMATION:

Observe the maximum stacking height of 2 pallets. The insulation material must be protected from the effects of moisture (rain) before, during and after processing. Undamaged transport packaging (shrink bonnets) are sufficient weather protection for short-term storage on the construction site.

7. DISPOSAL

EC WASTE CODE:

EC WASTE CODE: 03 01 05 17 02 01

8. SAFETY INSTRUCTIONS

No particular indications.

The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release the purchaser and processor from the obligation to convince themselves of the suitability of our products for the intended application with due care, which is general practice in trade and crafts. The general rules of construction technology must be observed. We reserve the right to make modifications to improve the product or its application. This edition supersedes all earlier editions.