



## TECHNICAL DATA SHEET

# KEIM LIGNOSIL®-BASE-W

## 1. PRODUCT DESCRIPTION

---

KEIM Lignosil-Base-W is a highly specialised primer for exterior wood. Based on a special combination of alkyd resins and silicate binders, KEIM Lignosil-Base-W consolidates the wood surface and ensures an optimal bond to the paint coating KEIM Lignosil-Color.

## 2. FIELD OF APPLICATION

---

Primer in the KEIM Lignosil system for weather protection of non-dimensionally stable and limited dimensionally stable wood components. KEIM Lignosil-Base-W do not use as top coat.

KEIM Lignosil-Base-W must always be recoated with KEIM Lignosil-Color.

Exception: On-site coating of cut surfaces in non-visible areas.

Hint:

Low-knot and low-resin woods are to be preferred. In the case of knotty woods, please note that knot cracks / loose knots can lead to paint damage in the knot area (spalling due to moisture penetration).

Not suitable for:

mechanically stressed surfaces; horizontal/inclined weathered surfaces such as: terrace and balcony floor, handrail stairs/balcony; Larchwood

## 3. PRODUCT PROPERTIES

---

- forced drying possible
- ready to use
- solidifying
- tested according to DIN EN 927
- good penetration property
- excellent moisture protection (within the KEIM Lignosil-System)
- optimal bond with the top coating
- water-based
- for the most part from renewable resources
- solvent-free
- low-odour

### MATERIAL CHARACTERISTICS:

- |             |                                     |
|-------------|-------------------------------------|
| - Density:  | approx. 1.0 - 1.1 g/cm <sup>3</sup> |
| - pH value: | approx. 7                           |
| - Solids:   | approx. 45 %                        |

## TECHNICAL DATA SHEET – KEIM LIGNOSIL®-BASE-W

### CLASSIFICATION:

- Classification according to: DIN EN 927
- Diffusion-equivalent air layer thickness (sd-value): < 0,5 m
- Norm Diffusionsäquivalente Luftschichtdicke DIN EN ISO 7783: DIN EN ISO 12572 wet-cup
- Water absorption value  $m_c \leq$ : 175 g/m<sup>2</sup>
- Standard for water absorption value  $m_c$  DIN EN 927-2: DIN EN 927-2

### COLOUR SHADES:

colourless

## 4. APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION:

The substrate must be sound, dry (wood moisture content below 18% according to technical information No. 18 by BFS), clean, free of dust, loose parts, oil and any other substances with separative properties. Remove loose and cracked knots and open resin areas and clean wood with suitable agent. Coating of old coatings is possible after inspection. However, it is recommended to remove old coatings as completely as possible. Weathered surfaces are to be sanded down to the sound wood. Oily wood should be cleaned with nitro thinner.

### APPLICATION CONDITIONS:

Ambient and substrate temperature  $\geq 8$  °C during application and drying. Do not apply in direct sunlight or on sun-heated substrates. Protect surfaces from direct sun, wind and rain during and after application.

### APPLICATION:

KEIM Lignosil-Base-W should be primed twice with a brush, roller or machine, e.g. with an airless device (nozzle  $\geq 512$  ), automatic brush or vacuum. New wood must always be primed on all sides before installation. When renovating technically intact old coatings (overhaul) and for surfaces with low stress, a single primer coat with KEIM Lignosil-Base-W can be applied. For heavily stressed surfaces and to achieve the longest service life, a double priming is recommended. Note: Please observe DIN EN 927. After drying, the primer is to be overcoated with Lignosil-Color as a top coat. Observe drying times!

Note: All cut surfaces must be protected against moisture by coating with KEIM Lignosil-Base-W!

Paint coating: The paint coating is applied twice, on the visible side and undiluted with Lignosil-Color.

### DRYING TIME:

Surface dry after 2 hours at the earliest (at 23 °C and 50% relative humidity) Can be overcoated after 8 hours at the earliest (at 23 °C and 50% RH). At higher relative humidity, layer thicknesses and/or lower temperatures, drying is delayed accordingly.

### CONSUMPTION:

approx. 0,1 l/m<sup>2</sup> as base coat.

These material consumption values are guide values for smooth substrates. Exact consumption values must be determined by means of test areas.

### CLEANING OF TOOLS:

Clean immediately with water.

## 5. PACKAGING

Container content	Unit of measure	Quantity on pallet	Type of container
20	l	22	tin bucket
5	l	96	tin bucket

## TECHNICAL DATA SHEET – KEIM LIGNOSIL®-BASE-W

Container content	Unit of measure	Quantity on pallet	Type of container
2.5	l	120	tin can

### 6. STORAGE

max. storage time	Storage conditions
6 months	keep container tightly sealed. cool frost-free protected from heat and direct sun.

### 7. DISPOSAL

For disposal information refer to section 13 of the safety data sheet.

**EC WASTE CODE:**

EC WASTE CODE: 08 01 12

### 8. SAFETY INSTRUCTIONS

Please, refer to the Material Safety Data Sheet.

### 9. GENERAL INFORMATION

The information on the diffusion-equivalent air layer thickness applies to two coats of KEIM Lignosil-Base-W and KEIM Lignosil-Color.

Cover surfaces not to be treated, especially glass, ceramics and natural stone. Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with plenty of water.

Mixing with products not part of the system or other foreign additives is not permitted.

### 10. CERTIFICATES & QUALITY SEALS



The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release the purchaser and processor from the obligation to convince themselves of the suitability of our products for the intended application with due care, which is general practice in trade and crafts. The general rules of construction technology must be observed. We reserve the right to make modifications to improve the product or its application. This edition supersedes all earlier editions.