



TECHNICAL DATA SHEET

KEIM REVERSIL-SCHLÄMME®

1. PRODUCT DESCRIPTION

KEIM Reversil-Schlämme is a highly filled, removable primer for the protection of historic paintings and substrates indoors. It can be removed later with water like KEIM Reversil, without damaging or distorting the substrate.

2. FIELD OF APPLICATION

KEIM Reversil-Schlämme can be used to smear or level cracked surfaces and structural differences, e.g. after plaster repairs. Suitable substrates are plaster, stucco, sandstone, sand-lime brick and firmly adhering old coatings. A wide variety of applications are possible in combination with the precisely coordinated product components of the KEIM Reversil system.

3. PRODUCT PROPERTIES

- reversible
- structure-equalising
- crack-bridging
- smudge-proof
- mineral matt
- QNG-konform
- highly permeable
- absolutely lightfast

MATERIAL CHARACTERISTICS:

- Density: approx. 1.5 - 1.6 g/cm³
- pH value: approx. 8

CLASSIFICATION:

- Diffusion-equivalent air layer thickness (sd-value): < 0,03 m

COLOUR SHADES:

white

4. APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION:

The substrate must be sound, solid, dry, clean and free from dust and grease. Highly absorbent or gypsum-containing substrates can be primed with KEIM Reverfix and thus reduced in their absorbency.

APPLICATION CONDITIONS:

Ambient and substrate temperature during application and drying must be ≥ 5 °C.

PREPARATION OF MATERIAL:

Stir up KEIM Reversil-Schlämme thoroughly before application.

TECHNICAL DATA SHEET – KEIM REVERSIL-SCHLÄMME®

CONSUMPTION:

approx. 0,5 kg/m² for a single coating.

These material consumption values are guide values for smooth substrates. Exact consumption values must be determined by means of test areas.

APPLICATION:

KEIM Reversil-Schlämme is painted or rolled on undiluted after stirring well. KEIM Reversil-Schlämme replaces the primer coat with KEIM Reversil white and can be finished opaque or glazing with KEIM Reversil. KEIM Reversil-Schlämme can also be mixed with KEIM Reversil in any ratio for the primer coat.

Final coat: Apply with undiluted KEIM Reversil.

Removal:

Pre-wet thoroughly with water and then wash off with clear water and a brush after approx. 10 minutes exposure time.

DRYING TIME:

Can be overcoated after 12 hours at the earliest (at 23°C and 50% RH). At higher relative humidity, layer thicknesses and/or lower temperatures, drying is delayed accordingly.

CLEANING OF TOOLS:

Clean immediately with water.

5. PACKAGING

Container content	Unit of measure	Quantity on pallet	Type of container
25	kg	24	bucket
5	kg	70	bucket

6. STORAGE

max. storage time	Storage conditions
12 months	cool frost-free keep container tightly sealed. protected from heat and direct sun.

7. DISPOSAL

For disposal information refer to section 13 of the safety data sheet.

Waste code: 08 01 11 *

8. SAFETY INSTRUCTIONS

Please, refer to the Material Safety Data Sheet. EU limit value for this product (Cat. A/a): 30 g/l.

This product contains: 0 - 3 g/l VOC.

GISCODE: BSW 50

9. GENERAL INFORMATION

Cover surfaces not to be treated, especially glass, ceramics and natural stone. Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with plenty of water.

Mixing with products not part of the system or other foreign additives is not permitted.

10. CERTIFICATES & QUALITY SEALS



The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release the purchaser and processor from the obligation to convince themselves of the suitability of our products for the intended application with due care, which is general practice in trade and crafts. The general rules of construction technology must be observed. We reserve the right to make modifications to improve the product or its application. This edition supersedes all earlier editions.