



TECHNICAL DATA SHEET

KEIM SOLDALAN®-ME

1. PRODUCT DESCRIPTION

KEIM Soldalan-ME is a highly specialised silicate facade paint based on a proven binder combination of silica sol and water glass with photocatalytic effect. This binder combination allows silicate coatings not only on mineral but also on a wide range of organic substrates – directly and without additional bonding bridges. The photocatalytic effect reduces harmful gases (e.g. NO_x, VOC's) and increases the self-cleaning ability. Filled and pigmented with weather-resistant fillers and purely inorganic pigments combines KEIM Soldalan-ME all the advantages of classic dispersion silicate paint with the substrate versatility of organically bonded KEIM Soldalan-ME paint systems also fulfils the requirements of DIN 18363 para. 2.4.1 "Dispersion silicate paint".

2. FIELD OF APPLICATION

KEIM Soldalan-ME is suitable for renovation and new coating of load-bearing, dispersion- and silicone resin-bound paints and plasters as well as for mineral substrates.

Not suitable for:

horizontal and inclined surfaces exposed to weathering; wood substrates; plasto-elastic coatings; saponifiable existing substrates; non-wettable substrates

3. PRODUCT PROPERTIES

- universally applicable
- photocatalytic
- reduces harmful gases (e.g. NO_x, VOC's) and organic pollution
- permeable
- highly water-repellent
- microporous
- antistatic, non-thermoplastic
- highly weather-resistant
- absolutely lightfast
- anti-fungal and anti-algae thanks to ideal moisture balance
- acid-proof
- fire behaviour: non-flammable (Class A2-s1,d0 as per EN 13501-1 acc. to classification report)
- no solvents added
- no plasticisers added

MATERIAL CHARACTERISTICS:

- Density: approx. 1.5 - 1.6 g/cm³
- Organic content: ≤ 5
- pH value: approx. 11

CLASSIFICATION:

- Classification according to: DIN EN 1062-1
- Classification according to VOB: Silicate emulsion paint according to DIN 18363 sec. 2.4.1
- Water vapour diffusion current density (V-value): ≥ 2000
- Diffusion-equivalent air layer thickness (sd-value): ≥ 0,01 m

TECHNICAL DATA SHEET – KEIM SOLDALAN®-ME

- Diffusion-equivalent air layer thickness class:	V1
- Test standard Diffusion equivalent air layer thickness:	DIN EN ISO 7783
- Water permeability:	< 0,1 kg/(m ² √h)
- Water permeability rate class:	W3
- Test standard Water permeability rate:	DIN EN 1062-3
- Gloss level at 85°:	matt
- Test standard Gloss level:	ISO 2813

COLOUR SHADES:

White and colour shades only with purely mineral, light-resistant pigments. Only factory tinting possible. When selecting the colour shade for ETICS, observe LRV ≥ 30.

4. APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION:

The substrate must be dry, sound, free from chalking, clean and dust-free. Loose parts of existing coatings must be removed mechanically or by high-pressure water jetting. Defective areas must be filled and texture-matched using a suitable repair material. Any sintered layers on new renders must be removed with KEIM Ätzflüssigkeit (lime remover) according to instructions. New render areas (repairs) are generally to be pretreated with KEIM Ätzflüssigkeit (lime remover) according to the specifications in the Technical Data Sheet. Strongly absorbing surfaces must be primed with KEIM Soldalit-Fixativ. Please, refer to the Technical Data Sheet of the primer regarding application.

In case of larger cracks or strong structural differences, a primer coat with KEIM Contact-Plus might be necessary instead of KEIM Soldalan-ME.

APPLICATION CONDITIONS:

Ambient and substrate temperature ≥ 5 °C during application and drying. Do not apply in direct sunlight or on sun-heated substrates. Protect surfaces from direct sun, wind and rain during and after application.

PREPARATION OF MATERIAL:

Stir up KEIM Soldalan-ME thoroughly before application.

APPLICATION:

KEIM Soldalan-ME can be painted, rolled or airless sprayed (nozzle: ≥ 435).

Primer coat: Apply KEIM Soldalan-ME in the normal case undiluted or depending on the absorbency of the substrate, diluted up to max. 5 % with KEIM Soldalit-Fixativ.

Final coat: Apply KEIM Soldalan-ME undiluted.

DRYING TIME:

Can be overcoated after 12 hours at the earliest (at 23 °C and 50% RH).

At higher relative humidity, layer thicknesses and/or lower temperatures, drying is delayed accordingly.

CONSUMPTION:

approx. 0,45 kg/m² for two coatings.

These material consumption values are guide values for smooth substrates. Exact consumption values must be determined by means of test areas.

CLEANING OF TOOLS:

Clean immediately with water.

TECHNICAL DATA SHEET – KEIM SOLDALAN®-ME

5. PACKAGING

Container content	Unit of measure	Quantity on pallet	Type of container
20	kg	32	bucket
5	kg	70	bucket

6. STORAGE

max. storage time	Storage conditions
12 months	cool frost-free keep container tightly sealed.

STORAGE INFORMATION:

Material residues from opened containers should be refilled into smaller containers to keep the air space in the bucket as low as possible.

7. DISPOSAL

For disposal information refer to section 13 of the safety data sheet.

EC WASTE CODE:

Waste code: 08 01 12

8. SAFETY INSTRUCTIONS

Please, refer to the Material Safety Data Sheet.

GISCODE:

GIS code: BSW 40

9. GENERAL INFORMATION

Cover surfaces not to be treated, especially glass, ceramics and natural stone. Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with plenty of water.

Mixing with products not part of the system or other foreign additives is not permitted.

10. CERTIFICATES & QUALITY SEALS



TECHNICAL DATA SHEET – KEIM SOLDALAN®-ME

The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release the purchaser and processor from the obligation to convince themselves of the suitability of our products for the intended application with due care, which is general practice in trade and crafts. The general rules of construction technology must be observed. We reserve the right to make modifications to improve the product or its application. This edition supersedes all earlier editions.



KEIMFARBEN GMBH

Keimstraße 16 / 86420 Diedorf / Tel. +49 821 4802-0 / Fax +49 821 4802-210
Frederik-Ipsen-Straße 6 / 15926 Luckau / Tel. +49 35456 676-0 / Fax +49 35456 676-38
www.keim.com / info@keimfarben.de