

Page 1/10

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 21.05.2021

Version number 13.0

Revision: 21.05.2021

SECTION 1: Identification of the substance/mixture and of the company/ undertaking

· 1.1 Product identifier

- Trade name: <u>KEIM FINE-FINISHING-MORTAR</u> (CONCRETAL-FEINSPACHTEL)
- 1.2 Relevant identified uses of the substance or mixture and uses advised against • Application of the substance / the mixture
- Dry mortar to be mixed with water and then used as a fine filler indoors and outdoors.
- · Uses advised against All other uses are not recommended.
- · 1.3 Details of the supplier of the safety data sheet

• Manufacturer/Supplier: KEIM MINERAL PAINTS LTD Santok Building / Deer Park Way, Donnington Wood GB-Telford, Shropshire TF2 7NA Tel +44 1952 231 250 / Fax +44 1952 231 251 www.keim.com / sales@keimpaints.co.uk

- **Further information obtainable from:** David Pratt Telefon: +44 1952 231250 E-Mail: sales@keimpaints.co.uk
- **1.4 Emergency telephone number:** GBK GmbH Global Regulatory Compliance Emergency number: +49(0)6132/84463

SECTION 2: Hazards identification

· 2.1 Classification of the substance or mixture

Classification according to Regulation (EC) No 1272/2008

Skin Irrit. 2 H315 Causes skin irritation.

Eye Dam. 1 H318 Causes serious eye damage.

STOT SE 3 H335 May cause respiratory irritation.

· 2.2 Label elements

- Labelling according to Regulation (EC) No 1272/2008
- The product is classified and labelled according to the CLP regulation.
- · Hazard pictograms



· Signal word Danger

- **Hazard-determining components of labelling:** Cement, portland, chemicals
- Hazard statements
- H315 Causes skin irritation.
- H318 Causes serious eye damage.

(Contd. on page 2)

GB



Page 2/10

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 21.05.2021

Version number 13.0

Revision: 21.05.2021

Trade name: KEIM FINE-FINISHING-MORTAR (CONCRETAL-FEINSPACHTEL)

(Contd. of page 1) H335 May cause respiratory irritation. **Precautionary statements** P280 Wear protective gloves/protective clothing/eye protection/face protection. P261 Avoid breathing dust. Use only outdoors or in a well-ventilated area. P271 P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Get immediate medical advice/attention. P315 P304+P340 IF INHALED: Remove person to fresh air and keep comfortable for breathing. IF ON SKIN: Wash with plenty of soap and water. P302+P352 P362 Take off contaminated clothing. P332+P313 If skin irritation occurs: Get medical advice/attention. 2.3 Other hazards This Product contains cement. Cement produces an alkaline reaction with moisture or water. Avoid contact with eyes and prolonged skin contact. · Results of PBT and vPvB assessment

- **PBT:** Not applicable
- · vPvB: Not applicable

SECTION 3: Composition/information on ingredients

· 3.2 Mixtures

· Description: Portland-cement, aggregate and additives

· Dangerous components:

CAS: 65997-15-1 Cement, portland, chemicals

25-50%

• Additional information: For the wording of the listed hazard phrases refer to section 16.

EINECS: 266-043-4 📀 Eye Dam. 1, H318; 🕐 Skin Irrit. 2, H315; STOT SE 3, H335

SECTION 4: First aid measures

· 4.1 Description of first aid measures

- General information: When seeing the doctor we suggest to present this safety data sheet.
- After inhalation: Supply fresh air; consult doctor in case of complaints.
- After skin contact:

Immediately wash with water and soap and rinse thoroughly.

Do not use solvents or thinners.

- If skin irritation continues, consult a doctor. After eye contact:
- Rinse opened eye for several minutes under running water. Then consult a doctor.
- After swallowing:
- Rinse mouth and throat well with water.

Do not induce vomiting; call for medical help immediately.

• **4.2 Most important symptoms and effects, both acute and delayed** No further relevant information available.

(Contd. on page 3)

GB



Page 3/10

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 21.05.2021

Version number 13.0

Revision: 21.05.2021

Trade name: KEIM FINE-FINISHING-MORTAR (CONCRETAL-FEINSPACHTEL)

(Contd. of page 2)

• **4.3 Indication of any immediate medical attention and special treatment needed** No further relevant information available.

SECTION 5: Firefighting measures

- · 5.1 Extinguishing media
- · Suitable extinguishing agents:
- Product itself does not burn. Co-ordinate fire-fighting measures to the fire surroundings.
- 5.2 Special hazards arising from the substance or mixture
- No further relevant information available.
- 5.3 Advice for firefighters
- · Specila protective equipment: Wear self-contained respiratory protective device.
- Additional information Dispose of fire debris and contaminated fire fighting water in accordance with official regulations. In case of fire do not breathe smoke, fumes and vapours.

SECTION 6: Accidental release measures

· 6.1 Personal precautions, protective equipment and emergency procedures Avoid contact with skin and eves. Avoid formation of dust. Use respiratory protective device against the effects of fumes/dust/aerosol. Respect the protection rules (see section 7 a. 8). Product forms slippery surface when combined with water. 6.2 Environmental precautions: Do not allow product to reach soil, sewage system or any water course. Follow local governmental rules and regulations. · 6.3 Methods and material for containment and cleaning up: Close drainages (risk of blocking) Danger of slipping! Avoid formation of dust. Ensure adequate ventilation. Pick up mechanically. Dispose of the material collected according to regulations. Clear contaminated areas thoroughly. 6.4 Reference to other sections

See Section 7 for information on safe handling. See Section 8 for information on personal protection equipment. See Section 13 for disposal information.

SECTION 7: Handling and storage

· 7.1 Precautions for safe handling

Avoid contact with skin and eyes.

(Contd. on page 4)

GB



Page 4/10

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 21.05.2021

Version number 13.0

Revision: 21.05.2021

Trade name: KEIM FINE-FINISHING-MORTAR (CONCRETAL-FEINSPACHTEL)

(Contd. of page 3	3)
Keep receptacles tightly sealed.	
Prevent formation of dust.	
Any unavoidable deposit of dust must be regularly removed. Ensure good ventilation/exhaustion at the workplace.	
See item 8 (8.2) for information about suitable protective equipment and technical precautions	
Respect the protection rules.	
· Information about fire - and explosion protection:	
The product is not flammable.	
No special measures required.	
• 7.2 Conditions for safe storage, including any incompatibilities	
Storage:	
Requirements to be met by storerooms and receptacles:	
Keep in the original containers in a cool and dry place.	
Store only in unopened original receptacles.	
 Information about storage in one common storage facility: Do not store together with acids. Further information about storage conditions: 	
Store in dry conditions.	
Protect from humidity and water.	
Avoid dust formations and deposits.	
Keep container tightly sealed.	
Store in cool, dry conditions in well sealed receptacles.	
• Storage class: 13	
• 7.3 Specific end use(s) No further relevant information available.	
	_
SECTION 8: Exposure controls/personal protection	

· 8.1 Control parameters

- Ingredients with limit values that require monitoring at the workplace:
- General dust limit (Germany): Long-term value: 1.25 * 10 ** mg / m³ 2 (II);

* respirable fraction ** inhalable fraction The national general dust limit value must be observed.

65997-15-1 Cement, portland, chemicals

- WEL Long-term value: 10* 4** mg/m³
 - *inhalable dust **respirable dust

DNELs

65997-15-1 Cement, portland, chemicals

- Inhalative Long-term systemic effects 1 mg/m³ (worker)
- Additional information: The lists valid during the making were used as basis.
- · 8.2 Exposure controls
- Individual protection measures, such as personal protective equipment
- · General protective and hygienic measures:

Vacuum clean contaminated clothing. Do not blow or brush off contamination. Avoid contact with the eyes and skin.

Do not inhale dust / smoke / mist.

(Contd. on page 5)



Page 5/10

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 21.05.2021

Version number 13.0

Revision: 21.05.2021

Trade name: KEIM FINE-FINISHING-MORTAR (CONCRETAL-FEINSPACHTEL)

In a dusty environment wear protective goggles. Tightly sealed goggles		(Contd. of page
Respiratory protection: In a dusty environment wear suitable facemask. Filter: FFP2 Hand protection Protective gloves Alkaline resistant gloves Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0.5 mm The selection of the suitable gloves does not only depend on the material, but also on further mail of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under praction conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Eddy protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
In a dusty environment wear suitable facemask. Filter: FFP2 Hand protection Protective gloves Alkaline resistant gloves Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0.5 mm The selection of the suitable gloves does not only depend on the material, but also on further main of quality and varies from manufacturer to manufacturer. As the product is a preparation of seven substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Eightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		contaminated clothing.
Filter: FFP2 Hand protection Protective gloves Alkaline resistant gloves Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0.5 mm The selection of the suitable gloves does not only depend on the material, but also on further material of quality and varies from manufacturer to manufacturer. As the product is a preparation of seves substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practi conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration tim is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
Hand protection Protective gloves Alkaline resistant gloves Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0.5 mm The selection of the suitable gloves does not only depend on the material, but also on further mai of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practi conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration tim is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		DIE TACEMASK.
Protective gloves Alkaline resistant gloves Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0.5 mm The selection of the suitable gloves does not only depend on the material, but also on further mat of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practi conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration tim is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
Alkaline resistant gloves Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0.5 mm The selection of the suitable gloves does not only depend on the material, but also on further main of quality and varies from manufacturer to manufacturer. As the product is a preparation of seven substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves at has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
Material of glovessuitable material e.g.:Nitrile impregnated cotton-glovesRecommended thickness of the material: $\geq 0.5 \text{ mm}$ The selection of the suitable gloves does not only depend on the material, but also on further material quality and varies from manufacturer to manufacturer. As the product is a preparation of sevessubstances, the resistance of the glove material can not be calculated in advance and has thereforeto be checked prior to the application.Penetration time of glove materialValue for the permeation: level ≥ 6 (480 min)The determined penetration times according to EN 16523-1:2015 are not performed under practicconditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration timeis recommended.The exact break trough time has to be found out by the manufacturer of the protective gloves at has to be observed.Eye/face protectionIn a dusty environment wear protective goggles.Body protection:Protective work clothingAfter contact with skin wash thoroughly with water and apply lotion.Environmental exposure controlsSee Section 12 and 6.2		
suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0.5 mm The selection of the suitable gloves does not only depend on the material, but also on further man of quality and varies from manufacturer to manufacturer. As the product is a preparation of seves substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves at has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
Nitrile impregnated cotton-gloves Recommended thickness of the material: $\geq 0.5 \text{ mm}$ The selection of the suitable gloves does not only depend on the material, but also on further material of quality and varies from manufacturer to manufacturer. As the product is a preparation of seven substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
Recommended thickness of the material: $\geq 0.5 \text{ mm}$ The selection of the suitable gloves does not only depend on the material, but also on further material of quality and varies from manufacturer to manufacturer. As the product is a preparation of severe substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
The selection of the suitable gloves does not only depend on the material, but also on further main of quality and varies from manufacturer to manufacturer. As the product is a preparation of seven substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Value for the permeation: level \geq 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		atorial . 0 E mm
of quality and varies from manufacturer to manufacturer. As the product is a preparation of sever substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration times is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
to be checked prior to the application. Penetration time of glove material Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practi conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
 Penetration time of glove material Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration times recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2 		
Value for the permeation: level ≥ 6 (480 min) The determined penetration times according to EN 16523-1:2015 are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration times is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
The determined penetration times according to EN 16523-1:2015 are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration times recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration tim is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		
has to be observed. Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		to be found out by the manufacturer of the protective gloves a
Eye/face protection In a dusty environment wear protective goggles. Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2		, , , , , , , , , , , , , , , , , , , ,
Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2	· Eye/face protection	
Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2	In a dusty environment wear protect	ctive goggles.
Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2	Tightly sealed goggles	
After contact with skin wash thoroughly with water and apply lotion. Environmental exposure controls See Section 12 and 6.2	Body protection:	
Environmental exposure controls See Section 12 and 6.2	Protective work clothing	
See Section 12 and 6.2		
		ls
No further relevant information available.		
	No further relevant information ava	ilable.
	See Section 12 and 6.2	
SECTION 9: Physical and chemical properties		al and chemical properties
9.1 Information on basic physical and chemical properties		0-11-1
9.1 Information on basic physical and chemical properties General Information	•	
9.1 Information on basic physical and chemical properties General Information Physical state Solid		
9.1 Information on basic physical and chemical properties General Information Physical state Solid Colour: Grey		
9.1 Information on basic physical and chemical properties General Information Physical state Solid Colour: Grey Odour: Odourless	· Odour threshold:	Not determined

Not determined

Not applicable. Not applicable

• Melting point/freezing point:

- · Boiling point or initial boiling point and boiling range Flammability

(Contd. on page 6)



Page 6/10

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 21.05.2021

Version number 13.0

Revision: 21.05.2021

Trade name: KEIM FINE-FINISHING-MORTAR (CONCRETAL-FEINSPACHTEL)

	(Contd. of page
Lower and upper explosion limit	
Lower:	Not applicable
Upper:	Not applicable
Flash point:	Not applicable
Auto-ignition temperature:	Product is not selfigniting.
Decomposition temperature:	Not determined
pH at 20 °C	11.5-13.5*
	mixed with water
Viscosity:	
Kinematic viscosity	Not applicable
Dynamic:	Not applicable
Solubility	
water:	Miscible
	WISCIDIE
Partition coefficient n-octanol/water (log	Not applicable
value)	Not applicable
Vapour pressure:	Not applicable.
Density and/or relative density	
Density:	Not determined
Relative density	Not determined
Vapour density	Not applicable.
9.2 Other information	* The values are for freshly produced materia
	and may change with the time.
Appearance:	
Form:	Powder
Important information on protection of hea	
and environment and on satety	
and environment, and on safety.	Not determined
Ignition temperature:	Not determined
Ignition temperature: Explosive properties:	Not determined Product does not present an explosion hazard.
Ignition temperature: Explosive properties: Change in condition	
Ignition temperature: Explosive properties: Change in condition Softening point/range	Product does not present an explosion hazard.
Ignition temperature: Explosive properties: Change in condition Softening point/range Oxidising properties:	Product does not present an explosion hazard. Not applicable
Ignition temperature: Explosive properties: Change in condition Softening point/range	Product does not present an explosion hazard.
Ignition temperature: Explosive properties: Change in condition Softening point/range Oxidising properties: Evaporation rate	Product does not present an explosion hazard. Not applicable Not applicable
Ignition temperature: Explosive properties: Change in condition Softening point/range Oxidising properties: Evaporation rate Information with regard to physical haze	Product does not present an explosion hazard. Not applicable Not applicable
Ignition temperature: Explosive properties: Change in condition Softening point/range Oxidising properties: Evaporation rate Information with regard to physical haze classes	Product does not present an explosion hazard. Not applicable Not applicable ard
Ignition temperature: Explosive properties: Change in condition Softening point/range Oxidising properties: Evaporation rate Information with regard to physical haze classes Explosives	Product does not present an explosion hazard. Not applicable Not applicable ard Void
Ignition temperature: Explosive properties: Change in condition Softening point/range Oxidising properties: Evaporation rate Information with regard to physical haze classes Explosives Flammable gases	Product does not present an explosion hazard. Not applicable Not applicable ard Void Void
Ignition temperature: Explosive properties: Change in condition Softening point/range Oxidising properties: Evaporation rate Information with regard to physical haze classes Explosives Flammable gases Aerosols	Product does not present an explosion hazard. Not applicable ard Void Void Void Void Void
Ignition temperature: Explosive properties: Change in condition Softening point/range Oxidising properties: Evaporation rate Information with regard to physical haze classes Explosives Flammable gases Aerosols Oxidising gases	Product does not present an explosion hazard. Not applicable ard Void Void Void Void Void Void Void Voi
Ignition temperature: Explosive properties: Change in condition Softening point/range Oxidising properties: Evaporation rate Information with regard to physical haze classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure	Product does not present an explosion hazard. Not applicable ard Void Void Void Void Void Void Void Voi
Ignition temperature: Explosive properties: Change in condition Softening point/range Oxidising properties: Evaporation rate Information with regard to physical haze classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids	Product does not present an explosion hazard. Not applicable Not applicable ard Void Void Void Void Void Void Void Voi
Ignition temperature: Explosive properties: Change in condition Softening point/range Oxidising properties: Evaporation rate Information with regard to physical haze classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids	Product does not present an explosion hazard. Not applicable ard Void Void Void Void Void Void Void Voi
Ignition temperature: Explosive properties: Change in condition Softening point/range Oxidising properties: Evaporation rate Information with regard to physical haze classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids	Product does not present an explosion hazard. Not applicable Not applicable ard Void Void Void Void Void Void Void Voi
Ignition temperature: Explosive properties: Change in condition Softening point/range Oxidising properties: Evaporation rate Information with regard to physical haze classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids	Product does not present an explosion hazard. Not applicable ard Void

(Contd. on page 7)

[–] GB



Page 7/10

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 21.05.2021

Version number 13.0

Revision: 21.05.2021

Trade name: KEIM FINE-FINISHING-MORTAR (CONCRETAL-FEINSPACHTEL)

		(Contd. of page
 Self-heating substances and mixtures Substances and mixtures, which emit 	Void	
flammable gases in contact with water	Void	
Oxidising liquids	Void	
Oxidising solids	Void	
· Organic peroxides	Void	
Corrosive to metals	Void	
· Desensitised explosives	Void	

SECTION 10: Stability and reactivity

• **10.1 Reactivity** Reacts with water alkaline and hardens.

· 10.2 Chemical stability Stable under normal conditions of storage and use.

Thermal decomposition / conditions to be avoided:

Stable at environment temperature.

No decomposition if used and stored according to specifications.

10.3 Possibility of hazardous reactions No dangerous reactions known.

• 10.4 Conditions to avoid Humidity

· 10.5 Incompatible materials: Acids

10.6 Hazardous decomposition products:

No hazardous decomposition products if stored and handled as prescribed.

SECTION 11: Toxicological information

· 11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008

· Acute toxicity

· LD/LC50 values relevant for classification:

65997-15-1 Cement, portland, chemicals

Dermal LD50 >2,000 mg/kg (rabbit)

Inhalative LC50/4 h >5 mg/l (rat)

· Skin corrosion/irritation Causes skin irritation.

· Serious eye damage/irritation Causes serious eye damage.

· during inhalation: Irritating to respiratory system.

· during swallowing: Irritant effect possible

· Respiratory or skin sensitisation

Product is reduced in chromate. Within the indicated storage time sensitization is not expected. **STOT-single exposure** May cause respiratory irritation.

• Other information (about experimental toxicology):

Experimental analysis are not available.

The product was not tested. The statements on toxicology have been derived from the properties of the individual components.

• Subacute to chronic toxicity:

• CMR effects (carcinogenity, mutagenicity and toxicity for reproduction) Not applicable

(Contd. on page 8)



Page 8/10

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 21.05.2021

Version number 13.0

Revision: 21.05.2021

Trade name: KEIM FINE-FINISHING-MORTAR (CONCRETAL-FEINSPACHTEL)

· 11.2 Information on other hazards

(Contd. of page 7)

· Endocrine disrupting properties

None of the ingredients is listed.

SECTION 12: Ecological information

- · 12.1 Toxicity
- · Aquatic toxicity: No further relevant information available.
- 12.2 Persistence and degradability No further relevant information available.
- 12.3 Bioaccumulative potential No further relevant information available.
- 12.4 Mobility in soil No further relevant information available.
- · 12.5 Results of PBT and vPvB assessment
- **PBT:** Not applicable
- · vPvB: Not applicable
- 12.6 Endocrine disrupting properties

The product does not contain substances with endocrine disrupting properties.

- 12.7 Other adverse effects
- · Additional ecological information:
- · AOX-indication:

According to our standard of knowledge the product does not contain any organic bounded halogen. The product has no influence on the waste water's AOX-value.

According to the formulation contains the following heavy metals and compounds from the EU guideline NO. 2006/11/EC:

According to our current data base the product does not consist of any heavy metals or substances of EU-directives 76/464/EWG.

General notes:

At present there are no ecotoxicological assessments.

The statements on ecotoxicology have been derived from the properties of the individual components.

Do not allow product to reach ground water, water course or sewage system.

Water hazard class 1 (German Regulation) (Self-assessment): slightly hazardous for water

SECTION 13: Disposal considerations

· 13.1 Waste treatment methods

- Recommendation

Disposal must be made according to official regulations.

Must not be disposed with household garbage. Do not allow product to reach sewage system.

Unused remainders of the product should be regarded as hazardous waste.

Recommendation for non-reusable residues: Mix with water and allow to harden.

Allow wet product and product sludge to harden and do not allow to get into drains or waterways.

· European waste catalogue

17 01 01 concrete

(Contd. on page 9)



Page 9/10

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 21.05.2021

Version number 13.0

Revision: 21.05.2021

Trade name: KEIM FINE-FINISHING-MORTAR (CONCRETAL-FEINSPACHTEL)

(Contd. of page 8)

· Uncleaned packaging:

Recommendation:

Disposal must be made according to official regulations.

Non contaminated packagings may be recycled.

· Recommended cleansing agents: Water, if necessary with cleansing agents.

SECTION 14: Transport information

 14.1 UN number or ID number ADR, IMDG, IATA 	Void
 14.2 UN proper shipping name ADR, IMDG, IATA 	Void
· 14.3 Transport hazard class(es)	
· ADR, IMDG, IATA · Class	Void
 14.4 Packing group ADR, IMDG, IATA 	Void
 14.5 Environmental hazards: Marine pollutant: 	No
· 14.6 Special precautions for user	Not applicable
 14.7 Maritime transport in bulk accordi IMO instruments 	ng to Not applicable
· Transport/Additional information:	No dangerous good in sense of these transport regulations.
· UN "Model Regulation":	Void

SECTION 15: Regulatory information

 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture

Labelling according to Regulation (EC) No 1272/2008
 Section 2 of this dependence of the section 2 of this dependence of the section 2 of this dependence of the section 2 of the section

For information on labelling please refer to section 2 of this document.

· Directive 2012/18/EU

· Named dangerous substances - ANNEX I None of the ingredients is listed.

· National regulations:

• Waterhazard class: Water hazard class 1 (Self-assessment): slightly hazardous for water.

(Contd. on page 10)



Page 10/10

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 21.05.2021

Version number 13.0

Revision: 21.05.2021

Trade name: KEIM FINE-FINISHING-MORTAR (CONCRETAL-FEINSPACHTEL)

· Other regulations, limitations and prohibitive regulations

· Please note:

TRGS 200 (Germany) TRGS 500 (Germany) TRGS 510 (Germany)

TRGS 900 (Germany)

• Substances of very high concern (SVHC) according to REACH, Article 57 Not applicable

• 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

Relevant phrases

H315 Causes skin irritation. H318 Causes serious eye damage. H335 May cause respiratory irritation. Department issuing SDS: KEIMFARBEN Germany, Product safety department Abbreviations and acronyms: ADR: Accord relatif au transport international des marchandises dangereuses par route (European Agreement Concerning the International Carriage of Dangerous Goods by Road) IMDG: International Maritime Code for Dangerous Goods IATA: International Air Transport Association GHS: Globally Harmonised System of Classification and Labelling of Chemicals EINECS: European Inventory of Existing Commercial Chemical Substances ELINCS: European List of Notified Chemical Substances CAS: Chemical Abstracts Service (division of the American Chemical Society) TRGS: Technische Regeln für Gefahrstoffe (Technical Rules for Dangerous Substances, BAuA, Germany) DNEL: Derived No-Effect Level (REACH) LC50: Lethal concentration, 50 percent LD50: Lethal dose, 50 percent PBT: Persistent, Bioaccumulative and Toxic SVHC: Substances of Very High Concern vPvB: very Persistent and very Bioaccumulative EC10: Effective concentration at 10% mortality rate. EC50: Half maximal effective concentration. LC10: Lethal concentration at 10% mortality rate. NOEC: No observed effect concentration. REACH: Registration, Evaluation and Authorisation of Chemicals (Regulation (EC) No.1907/2006) Skin Irrit. 2: Skin corrosion/irritation – Category 2 Eye Dam. 1: Serious eye damage/eye irritation - Category 1

STOT SE 3: Specific target organ toxicity (single exposure) – Category 3

** Data compared to the previous version altered.

(Contd. of page 9)

GB -