



TECHNICAL DATA SHEET

FKD-MAX C2

1. PRODUCT DESCRIPTION

Rock wool insulation boards in accordance with DIN EN 13162.

2. FIELD OF APPLICATION

Facade insulation boards for KEIM external thermal insulation composite systems according to system approval: Z-33.43-185; Z-33.47-727; Z-33.46-1187; Z-33.49-1505

Generally approved by the building authorities for: exterior walls; basement ceilings.

Suitable for: Masonry or concrete, rendered and unrendered; panel material in timber construction; ETICS upgrade system.

Application type according to DIN 4108-10: WAP-zh; DI.

The complete ETIC system is non-combustible, class A2, s1-d0 in accordance with DIN EN 13501-1. Suitable for building heights up to 100 m. Permissible building height according to the State Building Code.

Not suitable for: horizontal and inclined surfaces exposed to weathering; metallic substrates; saponifiable existing substrates.

3. PRODUCT PROPERTIES

- with improved heat protection
- both sides coated for efficient gluing and reinforcing
- easy to use
- fire behaviour: non-flammable, class A1 according to EN 13501-1
- for increased sound insulation
- harmless to health
- completely recyclable
- resistant to aging
- The insulation panels comply with the high standards of the VDPM e.V. (association for insulation systems, renders and mortars)
- Externally monitored by the MPA University Stuttgart
- Externally monitored by Forschungsinstitut für Wärmeschutz e.V. München

MATERIAL CHARACTERISTICS:

- | | |
|---|---|
| - CE marking code: | MW-EN 13162 T5-DS(70,-)- DS(70,90)-CS(10)20-TR7,5-WSWL(P)-MU1 |
| - Rated value of thermal conductivity: | 0.035 W/mK |
| - Nominal value of thermal conductivity λ_D : | 0.034 W/mK |
| - Panel size: | 1200 x 400 mm |
| - Panel thickness: | 60 - 300 mm |
| - Edge formation: | square |
| - Bulk density according to EN 1602: | approx. 105 kg/m ³ |
| - Melting point: | ≥ 1000 °C |
| - Glow tolerance according to DIN EN 16733: | no tendency to continuous smouldering |
| - Flow resistance per unit length: | ≥ 40 kPa s/m ² |
| - Water absorption at long-term partial immersion: | WL(P) ≤ 3,0 kg/m ² |
| - Compressive stress at 10% compression: | CS(10) ≥ 20 kPa |
| - Tensile strength perpendicular to the panel plane: | TR7,5 ≥ 7,5kPa |

TECHNICAL DATA SHEET – FKD-MAX C2

| | |
|------------------------|---------------|
| - Thickness tolerance: | T5 +3 / -1 mm |
| - Width tolerance: | W2 ±2 mm |
| - Length tolerance: | L5 ±5 mm |
| - Squareness: | S5 ±5 mm/m |
| - Planarity: | P ±3 mm/m |
| - Colour shade: | yellow-brown |

4. APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION:

The substrate must be strong, dry, clean, sound and free from adhesion-reducing residues. The permanent compatibility of any existing coatings with the adhesive mortar must be examined by an expert. The insulation panel may also be used as a basement ceiling insulation panel: Rusty steel beams or damp areas must not be covered with insulation until the cause itself has been properly remedied.

APPLICATION CONDITIONS:

Ambient and substrate temperature during application and drying from ≥ 5 °C to ≤ 30 °C. Do not apply in direct sunlight or on sun-heated substrates. Protect surfaces from direct sun, wind and rain during and after application.

APPLICATION:

Cut to size using an insulation knife or a suitable insulation saw.

GLUING:

The insulation panels are butted tightly and glued in a bond from bottom to top. Apply the appropriate adhesive mortar to the insulation panels using the bead-and-dot method or over the entire surface. Push the boards into place. At the edges of the building, the insulation panels are glued offset. Apply the system's adhesive mortar to the insulation panels using the bead-and-dot method, ensuring an adhesion of min. 40 %. The insulation panels may also be adhered in 2 layers. The second layer of insulation panels is glued over the entire surface and in a staggered bond pattern (starting with half a row of panels). Adhesive surface proportion from 220 mm insulation thickness: min. 40 %. On panel materials in wood construction, the insulation panels are glued over the entire surface with the adhesive filler Klebespachtel. For this purpose, the adhesive filler is applied to the substrate or to the insulation panels with a notched trowel. Immediately after applying the adhesive, the insulation panels must be glued to the substrate. Closing of unavoidable defects and joints up to 5 mm wide with Iso Top Thermfoam B1 is permissible. General instruction with regard to gluing: Do not apply adhesive to the panel joints. Do not create an insulation panel joint over a joint in the substrate underneath. The insulation panel may also be used as a basement ceiling insulation panel: Apply Pulverkleber-90 with a notched trowel ≥ 10 mm to the full surface of the insulation panel, alternatively to the substrate, using the comb-bed method, and then float it into the adhesive bed with slight pressure. For full-surface bonding, it is recommended to apply adhesive mortar to both the insulation panel and the substrate (floating-buttering method). The insulation panels must be applied tightly to the substrate, cavities are not permissible.

DOWELING:

Check the adhesion of the insulation panels after at least 3 days. Insulation panels that are not bonded or damaged must be replaced. Anchoring is carried out in glued and dowelled ETICS systems with generally approved ETICS fasteners according to DIN EN 1991-1-4/NA. The required fastener quantity depends on the building height and the respective wind zone in which the object is located. The minimum distance between anchor shank and board edge is min. 150 mm, the minimum distance between anchor shank and anchor shank is min. 200 mm. For further information, please refer to our ETICS Technical Guide, Chapter #8, ETICS Wind Suction Loads. The insulation panel may also be used as a basement ceiling insulation panel: Without fire protection requirements: The insulation panels may only be glued to new substrates up to a maximum weight per unit area of 15 kg/m² (including any final coating). In the case of insufficiently load-bearing substrates (old substrates) or if the permissible weight per unit area is exceeded, dowelling is carried out using ETICS anchors approved by the general building authorities or by the European authorities. Minimum number of anchors: 2 anchors per insulation board cut. With fire protection requirements: If necessary, dowel with the basement ceiling insulation screw DDS-Z and the basement ceiling insulation washer DDT.

REINFORCEMENT:

Notes on the installation of field boundary joints for insulation board thicknesses > 200 mm:

The field sizes without expansion joints are 10 m x 12 m or 120 m² for thick layer systems (base plaster + finishing coat =

TECHNICAL DATA SHEET – FKD-MAX C2

total plaster thickness from 10 mm). The field sizes without expansion joints are 50 m x 25 m for thin-layer systems (under-plaster finishing coat = total plaster thickness up to 9 mm).

Notes on the installation of field boundary joints for insulation board thicknesses ≤ 200 mm and recessed anchor installation: The field sizes without expansion joints are 50 m x 25 m for ETIC systems with STR U 2G. The corresponding field sizes are to be determined object-specifically by the planner.

5. PACKAGING / TECHNICAL DATA

| Panel thickness [mm] | Dynamic stiffness s' [MN / m ³] | m ² per bundle | m ² per pallet | Bundle per pallet |
|----------------------|---|---------------------------|---------------------------|-------------------|
| 60 | 13 | 1.92 | 19.2 | 10 |
| 80 | 11 | 1.44 | 14.40 | 10 |
| 100 | 8 | 0.96 | 11.52 | 12 |
| 120 | 7 | 0.96 | 9.60 | 10 |
| 140 | 6 | 0.96 | 7.68 | 8 |
| 160 | 5 | 0.96 | 5.76 | 6 |
| 180 | 5 | 0.96 | 5.76 | 6 |
| 200 | 4 | 0.96 | 5.76 | 6 |
| 220* | 4 | 0.48 | 4.80 | 10 |
| 240* | 3 | 0.48 | 4.80 | 10 |
| 260* | 3 | 0.48 | 3.84 | 8 |
| 280* | 3 | 0.48 | 3.84 | 8 |
| 300* | 3 | 0.48 | 3.84 | 8 |

PACKAGING / TECHNICAL DATA ADDITIONAL INFORMATION:

* Delivery time on request. KEIMFARBEN must be informed of the use in ETIC systems.

6. STORAGE

| max. storage time | Storage conditions |
|-------------------------|-----------------------------------|
| no maximum storage time | dry protect against weathering |

STORAGE INFORMATION:

Please note max. stacking height of 2 m. Transport packaging is not sufficient weather protection.

7. DISPOSAL

EC WASTE CODE:

Waste code: 17 06 04

8. SAFETY INSTRUCTIONS

Safety instructions UZ 140: Wear protective gloves / protective clothes / eye protection/ face protection. In case of contact with eyes: Rinse cautiously with water for several minutes. Remove any contact lenses if possible. Continue to rinse. Get immediate medical advice/attention. / Keep children away from fresh render. / Always comply with work safety instructions.

The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release the purchaser and processor from the obligation to convince themselves of the suitability of our products for the intended application with due care, which is general practice in trade and crafts. The general rules of construction technology must be observed. We reserve the right to make modifications to improve the product or its application. This edition supersedes all earlier editions.



KEIMFARBEN GMBH

Keimstraße 16 / 86420 Diedorf / Tel. +49 821 4802-0 / Fax +49 821 4802-210
Frederik-Ipsen-Straße 6 / 15926 Luckau / Tel. +49 35456 676-0 / Fax +49 35456 676-38
www.keim.com / info@keimfarben.de