



## TECHNICAL DATA SHEET

# KEIM GRANITAL®-GROB

## 1. PRODUCT DESCRIPTION

---

KEIM Granital-Grob is a highly filled silicate-based priming paint according to VOB/C DIN 18363 Para. 2.4.1 (dispersion silicate paint) with a slightly slurring effect for primer coats on difficult substrates. KEIM Granital-Grob closes hairline cracks and equalises structures. KEIM Granital-Grob contains absolutely lightfast, inorganic pigments and mineral fillers. KEIM Granital-Grob is awarded with the Cradle to Cradle Certified®-Certificate Silver and the C2C Certified Material Health Certificate™ Gold.

## 2. FIELD OF APPLICATION

---

KEIM Granital-Grob is used as a primer or base and intermediate coat in the KEIM Granital system. KEIM Granital-Grob is used on mineral substrates that show hairline cracks and/or structural differences.

In combination with the other, precisely coordinated product components of the KEIM Granital system, a wide variety of applications are possible.

Not suitable for:

substrates with salt efflorescences; saponifiable existing substrates; horizontal and inclined surfaces exposed to weathering; plasto-elastic coatings; Finishing coats (color shades are lighter than the original shades in the color fan due to the manufacturing process)

## 3. PRODUCT PROPERTIES

---

- economical in consumption
- non-film forming
- mineral matt
- environmentally friendly
- structure-equalising
- Cradle to Cradle Certified®-Certificate Silver
- C2C Certified Material Health Certificate™ Gold
- highly water-repellent
- highly permeable
- highly weather-resistant
- resistant against industrial emissions
- anti-fungal and anti-algae thanks to ideal moisture balance
- no solvents added

### MATERIAL CHARACTERISTICS:

- Density: approx. 1.5 - 1.7 g/cm<sup>3</sup>
- pH value: approx. 11
- Colour fastness (Fb-code pursuant to BFS Leaflet No. 26): A1

### CLASSIFICATION:

- Classification according to: DIN EN 1062-1
- Classification according to VOB: Silicate emulsion paint according to DIN 18363 sec. 2.4.1
- Diffusion-equivalent air layer thickness (sd-value): ≤ 0,01 m
- Diffusion-equivalent air layer thickness class: V1

## TECHNICAL DATA SHEET – KEIM GRANITAL®-GROB

- Test standard Diffusion equivalent air layer thickness: DIN EN ISO 7783
- Gloss level at 85°: matt
- Test standard Gloss level: ISO 2813

### COLOUR SHADES:

White and colour shades only with purely mineral, light-resistant pigments. DELIMITER\_WHITESPACE Note: Filled paint material is not suitable for finish coats because the colours are lighter than original shades. On-site tinting exclusively with KEIM colour concentrates.

## 4. APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION:

The substrate must be dry, sound, free from chalking, clean and dust-free. Loose parts of existing coatings must be removed mechanically or by high-pressure water jetting. Defective areas must be filled and texture-matched using a suitable repair material. Any sintered layers on new renders must be removed with KEIM Ätzflüssigkeit (lime remover) according to instructions. New render areas (repairs) are generally to be pretreated with KEIM Ätzflüssigkeit (lime remover) according to the specifications in the Technical Data Sheet. Strongly absorbing surfaces must be primed with KEIM Spezial-Fixativ. Please, refer to the Technical Data Sheets of the primer regarding application and dilution. Sound, organic, existing coatings must be pre-coated with KEIM Contact-Plus as bonding bridge. Old coatings that are plasto-elastic or susceptible to saponification are not suitable for coating. Old, film-forming coatings that are not sound or hinder vapour diffusion must be removed with the paint stripper KEIM Dispersionsentferner or by mechanical methods. In case of larger cracks or strong structural differences, a primer coat with KEIM Contact-Plus might be necessary instead of KEIM Granital-Grob. A pretreatment with KEIM Silangrund is recommended for surfaces exposed to high moisture or weathering.

### APPLICATION CONDITIONS:

Ambient and substrate temperature  $\geq 5$  °C during application and drying. Do not apply in direct sunlight or on sun-heated substrates. Protect surfaces from direct sun, wind and rain during and after application.

### PREPARATION OF MATERIAL:

Stir up KEIM Granital-Grob thoroughly before application.

### APPLICATION:

KEIM Granital-Grob can be painted, rolled or sprayed (nozzle:  $\geq 443$ , for further information see TM on airless technology). On difficult, poorly and/or differently absorbent substrates, Special Fixative (Spezial-Fixativ) KEIM is recommended as a thinner.

Primer coat: For the primer coat, application with a roller or brush is recommended. Apply KEIM Granital-Grob in the normal case undiluted or depending on the absorbency of the substrate, diluted up to max. 20 % with KEIM Spezial-Fixativ.

Final coat: Apply with undiluted KEIM Granital. Three coats are recommended in the event of very heavy use.

### DRYING TIME:

Can be overcoated after 12 hours at the earliest (at 23 °C and 50% RH). At higher relative humidity, layer thicknesses and/or lower temperatures, drying is delayed accordingly. DELIMITER\_WHITESPACE After pretreatment with KEIM Silangrund, the base coat should be applied after approx. 4 hours.

### CONSUMPTION:

approx. 0,2 kg/m<sup>2</sup> for a single coating.

These material consumption values are guide values for smooth substrates. Exact consumption values must be determined by means of test areas.

### CLEANING OF TOOLS:

Clean immediately with water.

## TECHNICAL DATA SHEET – KEIM GRANITAL®-GROB

### 5. PACKAGING

| Container content | Unit of measure | Quantity on pallet | Type of container |
|-------------------|-----------------|--------------------|-------------------|
| 25                | kg              | 24                 | bucket            |
| 5                 | kg              | 70                 | bucket            |

### 6. STORAGE

| max. storage time | Storage conditions                                   |
|-------------------|--|
| 12 months         | cool<br>frost-free<br>keep container tightly sealed. |

### 7. DISPOSAL

For disposal information refer to section 13 of the safety data sheet.

#### EC WASTE CODE:

Waste code: 08 01 12

### 8. SAFETY INSTRUCTIONS


Please, refer to the Material Safety Data Sheet.

### 9. GENERAL INFORMATION

Cover surfaces not to be treated, especially glass, ceramics and natural stone. Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with plenty of water.

Mixing with products not part of the system or other foreign additives is not permitted.

### 10. CERTIFICATES & QUALITY SEALS



The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release the purchaser and processor from the obligation to convince themselves of the suitability of our products for the intended application with due care, which is general practice in trade and crafts. The general rules of construction technology must be observed. We reserve the right to make modifications to improve the product or its application. This edition supersedes all earlier editions.