



TECHNICAL DATA SHEET

KEIM MYCAL[®]-CS-DÄMMKEIL

1. PRODUCT DESCRIPTION

Insulation wedge made of calcium silicate, approved by the building authorities according to ETA-15/0340.

2. FIELD OF APPLICATION

For mould remediation and moisture regulation in interior rooms. The Mycal-CS panel prevents the formation of condensation on the surface and thus contributes to the prevention of mould growth and the improvement of the indoor climate. Can be used as flank insulation for the ceiling and wall connection area.

Application on : interior walls; ceiling surfaces, indoors; window and door reveals.

Suitable for: Masonry or concrete, rendered and unrendered; mineral render; natural stone; timber frame .

Not suitable for: gypsum renders; wood substrates; metallic substrates; organic substrates.

3. PRODUCT PROPERTIES

- easy to use
- fire behaviour: non-flammable, class A1 according to EN 13501-1
- alkaline
- low environmental impact
- resistant to aging
- Externally monitored by the MPA Nordrhein-Westfalen

MATERIAL CHARACTERISTICS:

- | | |
|---|--------------------------------------|
| - Panel size: | 1250 x 500 mm |
| - Panel thickness: | 30/8 mm |
| - Edge formation: | square |
| - Bulk density: | ≤ 180 kg/m ³ |
| - Reference moisture content at 80%
rel. humidity: | 0.007 m ³ /m ³ |
| - Saturation moisture: | 0.929 m ³ /m ³ |
| - Compressive strength: | ≥ 1000 kPa |
| - Compressive stress at 10%
compression: | CS(10) ≥ 1000 kPa |
| - Thickness tolerance: | T2 ±2 mm/m |
| - Width tolerance: | W2 ±2 mm |
| - Length tolerance: | L2 ±2 mm |
| - Squareness: | S ≤ 4 mm/m |
| - Planarity: | S ≤ 2 mm |
| - Water absorption coefficient w: | 0,765 kg/(m ² √h) |
| - Colour shade: | light grey |

4. APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION:

The substrate must be strong, dry, clean, sound and free from adhesion-reducing residues and must not be too absorbent. The permanent compatibility of any existing coatings with the adhesive mortar must be examined by an expert. Substrates containing gypsum as well as vapour-tight coatings, wallpapers or similar must be removed. Highly absorbent substrates must

TECHNICAL DATA SHEET – KEIM MYCAL®-CS-DÄMMKEIL

be sufficiently prewetted. Unevenness of up to 1 cm/m may be bridged. Larger unevenness must be mechanically levelled or by applying a render in accordance with DIN EN 998-1.

APPLICATION:

Cut to size with a fine-toothed saw.

GLUING:

All connecting joints are made airtight with a joint sealing tape. An edge insulation strip must be inserted at the connection to floors and moisture-sensitive components. Before applying the adhesive, prewet the insulation panels with approx. 0.75 - 1.0 l water per panel. The panels are butted tightly and glued in a bond from bottom to top. Apply the system-specific adhesive mortar to the entire surface of the insulation panels, to the substrate, or to the insulation panels and the substrate using the floating-buttering method. Push the boards into place. At the edges of the building, the insulation panels are glued offset. General instruction with regard to gluing: Do not apply adhesive to the panel joints. System supplements are also possible across systems with Multipor Wedge (insulation wedge), Multipor Reveal (reveal panel), Mycal-CS-Dämmkeil (insulation wedge) or Mycal-CS-Laibungsplatte (reveal panel).

DOWELING:

Check the adhesion of the insulation panels after at least 3 days. Insulation panels that are not bonded or damaged must be replaced. In the case of subsequent tiling work, the panels are additionally fastened through the mesh with suitable screw anchors and finished with another layer of KEIM Universalputz.

REINFORCEMENT:

Prime the room-side panel surface of the Mycal-CS panels over the entire surface with a brush or by spraying with either CS-Primer or Mycal-Fix. Allow a waiting time of 24 hours before the next work step. After a sufficient setting time of the adhesive, apply the mixed, system-specific reinforcing mortar evenly to the insulation panels, preferably with a 10 mm toothed trowel. Embed the system-specific KEIM Glasfaser-Gittermatte (glass fibre mesh), overlap the edges by 10 cm and fill wet-in-wet with system-specific reinforcing mortar. The system-specific KEIM Glasfaser-Gittermatte should be embedded in the middle (layer thicknesses up to 6 mm) or in the upper third (layer thicknesses from 6 mm). Thickness of the reinforcement layer should be approx. 4 mm.

5. PACKAGING / TECHNICAL DATA

Panel size [mm]	Panel thickness [mm]	m ² per pallet
1250 x 500	30/8	2.5

6. STORAGE

max. storage time	Storage conditions
no maximum storage time	dry protect against weathering

7. DISPOSAL

EC WASTE CODE:

Waste code: 17 06 04

8. SAFETY INSTRUCTIONS

no particular indications

9. CERTIFICATES & QUALITY SEALS



The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release the purchaser and processor from the obligation to convince themselves of the suitability of our products for the intended application with due care, which is general practice in trade and crafts. The general rules of construction technology must be observed. We reserve the right to make modifications to improve the product or its application. This edition supersedes all earlier editions.



KEIMFARBEN GMBH

Keimstraße 16 / 86420 Diedorf / Tel. +49 821 4802-0 / Fax +49 821 4802-210
Frederik-Ipsen-Straße 6 / 15926 Luckau / Tel. +49 35456 676-0 / Fax +49 35456 676-38
www.keim.com / info@keimfarben.de