



TECHNICAL DATA SHEET

KEIM TURADO 0.3

1. PRODUCT DESCRIPTION

KEIM Turado 0.3 is a universally applicable natural white renovation bonded render for interior and exterior use, based on lime cement. KEIM Turado 0.3 Corresponds to mortar group GP CS III according to DIN EN 998-1.

2. FIELD OF APPLICATION

Mineral fine plaster for flat, finely felted surfaces, e.g. in reveals and flaps on doors and windows as well as in the base area. KEIM Turado 0.3 Can be used universally on load-bearing mineral substrates and old plasters of mortar groups CS II, CS III and CS IV, synthetic resin-bonded paints and plasters in interior and exterior areas.

KEIM Turado 0.3 is suitable for covering and levelling load-bearing old plasters or paints in layer thicknesses per layer up to approx. 5 mm, as an embedding mortar for fabric reinforcement (e.g. with KEIM glass fibre mesh mat) for smaller surfaces.

Not suitable:

saponifiable existing substrates; non-wettable substrates; plasto-elastic coatings; ETICS

3. PRODUCT PROPERTIES

- very good stability
- universally applicable
- for interior and exterior use
- excellent application properties
- very easy to smoothen
- very good adhesion
- permeable
- fire behaviour: non-flammable (A1)

MATERIAL CHARACTERISTICS:

- Maximum grain size: 0.3 mm

CLASSIFICATION:

- Classification according to: DIN EN 998-1
- Plaster type: GP
- Compressive strength category: CS III 3,5 -7,5 N/mm²
- Adhesive tensile strength: $\geq 0,2$ N/mm²
- Fracture pattern Adhesive tensile strength: A B
- Test standard Adhesive tensile strength: DIN EN 1015-12
- Water absorption class: W2
- Test standard Water absorption: DIN EN 1015-18
- Water vapour diffusion resistance value (μ -value): ≤ 15

4. APPLICATION INSTRUCTIONS

TECHNICAL DATA SHEET – KEIM TURADO 0.3

SUBSTRATE PREPARATION:

The substrate must be strong, dry, clean, sound and free from adhesion-reducing residues and must not be too absorbent. Separating substances, e.g. shuttering oil residues on concrete surfaces, must be removed by suitable means. Equalise strong unevenness with suitable material of the same type.

APPLICATION CONDITIONS:

Ambient and substrate temperature ≥ 5 °C during application and drying. Do not apply in direct sunlight or on sun-heated substrates. Protect surfaces from direct sun, wind and rain during and after application.

PREPARATION OF MATERIAL / MIXING & CONVEYING:

Mix KEIM Turado 0.3 with approx. 7.0 - 7.25 l (specification per bag) of clean water with a power stirrer to a stiff-plastic consistency without lumps and allow to mature briefly. Do not remix already stiffened material with water. Application can be performed by hand, via continuous mixer or rendering machine.

APPLICATION:

Apply mixed KEIM Turado 0.3 quickly with suitable tools in uniform layer thickness.

LAYERING SYSTEM:

Application in one or several layers, min. 3 mm and max. 5 mm layer thickness per layer. If greater layer thicknesses are required, it is recommended to use KEIM Turado in advance and to apply the finishing render layer with Turado 0.3.

TOP RENDER:

When using KEIM Turado 0.3 as finishing plaster, the surface can be felted with a sponge board after sufficient consolidation. Free texturing or washing is also possible.

AFTERTREATMENT:

KEIM Turado 0.3 must be protected from drying out too quickly due to sun or wind, or kept moist if necessary.

FINISHING:

Allow to stand before applying a coat.

SETTING TIME:

at least 1 day per mm render thickness (depending on temperature and relative humidity). When used as top coat render, allow to set for at least 5 days before coating. (If the standard rule of 1 day per mm results in longer setting times due to the layer thickness, the longer setting time must then be observed before painting).

CONSUMPTION:

approx. 1,4 kg/m² per mm

These material consumption values are guide values for smooth substrates. Exact consumption values must be determined by means of test areas.

CLEANING OF TOOLS:

Clean tools, machines and mixers immediately after use with water. In hardened state only a mechanical removal is possible.

5. PACKAGING

Container content	Unit of measure	Quantity on pallet	Type of container
25	kg	42	bag

6. STORAGE

max. storage time	Storage conditions
12 months	dry

TECHNICAL DATA SHEET – KEIM TURADO 0.3

7. DISPOSAL

For disposal information refer to section 13 of the safety data sheet.

EC WASTE CODE:

Waste code: 17 01 01

8. SAFETY INSTRUCTIONS

Please, refer to the Material Safety Data Sheet.

9. GENERAL INFORMATION

Cover surfaces not to be treated, especially glass, ceramics and natural stone. Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with plenty of water.

Mixing with products not part of the system or other foreign additives is not permitted.

The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release the purchaser and processor from the obligation to convince themselves of the suitability of our products for the intended application with due care, which is general practice in trade and crafts. The general rules of construction technology must be observed. We reserve the right to make modifications to improve the product or its application. This edition supersedes all earlier editions.